



# Kerapoxy



**Two-component acid-resistant epoxy grout (available in 26 colours) for joints of at least 3 mm. Can also be used as an adhesive**

#### **CLASSIFICATION IN COMPLIANCE WITH EN 13888**

Kerapoxy is a reaction resin (R) grout (G) of class RG.

#### **CLASSIFICATION IN COMPLIANCE WITH EN 12004**

Kerapoxy is an improved (2) reaction resin adhesive (R) and slip resistant (T) of class R2T.

#### **WHERE TO USE**

Indoor and outdoor grouting of ceramic tile and natural stone floors and walls. Also suitable for acid-resistant bonding and rapid setting of ceramic tiles, stone materials, fibre-cement, concrete and any other building material on all types of substrates normally used in construction.

#### **Some application examples**

- Grouting floors and walls in the food industry (dairies, abattoirs, breweries, wine-cellars, conserved-food plants, etc.), shops and areas where hygiene is required (ice-cream shops, butchers, fish vendors, etc.).
- Grouting industrial floors and walls (electrical industries, tanneries, battery rooms, paper-mills, etc.), where high mechanical resistance and resistance to acid attack is required.
- Grouting swimming pools; particularly suitable for basins containing salt or thermal water.
- Grouting tanks containing aggressive chemicals (purification plants, etc.).



# Kerapoxy



Grouting of single fired tile wall with a float



Finishing of single fired tile wall with a Scotch-Brite® pad



Finishing of single fired tile wall with a sponge

- Grouting ceramic tiles on laboratory benches, kitchen work surfaces, etc.
- Acid-resistant bonding of tiles (used as an adhesive in compliance with class R2T specification according to the EN 12004 standard).
- Bonding marble doorsteps and window-sills.
- Bonding tiles in plastic reinforced by fibre glass swimming pools.
- Bonding special pieces of tiles.

## TECHNICAL CHARACTERISTICS

**Kerapoxy** is a two-component epoxy-resin-based product with silica sand and special components, with excellent resistance to acids and excellent cleanability.

The following features are obtained when used correctly:

- Excellent mechanical and chemical resistance, therefore excellent durability.
- A smooth final surface with low water absorption, therefore easy to clean; ensures hygiene.
- Easy workability and finishing.
- Becomes very hard and is highly resistant to heavy traffic.
- No shrinkage, therefore absence of cracks and fissures.
- Uniform colours that are resistant to ultra-violet rays and atmospheric agents.
- Excellent bonding.

## RECOMMENDATIONS

- Because of the tessera's reduced thickness, **Kerapoxy** can also be used for grouting glass mosaics with joints less than 3 mm.
- When grouting ceramic tile floors and walls subject to oleic acid attack (e.g. ham and sausage industries, oil-mills, etc.) and aromatic hydrocarbon, use **Kerapoxy SP**, available in beige.
- For flexible expansion joints or joints subject to movement use an elastic sealant from the MAPEI range (e.g. **Mapesil AC**, **Mapesil LM** or **Mapeflex PU21**).
- **Kerapoxy** does not ensure perfect adhesion when used for grouting tiles with wet edges or contaminated with cement, dust, oil, grease, etc.
- Unglazed klinker tiles should be grouted with the same colour tone **Kerapoxy**. All other colours should be used only with glazed tiles.
- Do not use **Kerapoxy** for grouting terracotta tiles because they are difficult to clean.
- Make preliminary sample tests before grouting porcelain tiles with a contrasting colour of **Kerapoxy** (e.g. black on white).

- Always make preliminary sample tests before grouting stone materials or smoothed porcelain.
- Do not add water or any solvents to **Kerapoxy** to make it more fluid.
- Use the product in temperatures between +12°C and +30°C.
- The quantities are already in the correct proportions, therefore mistakes cannot be made. Do not use parts of the product mixing the two components at a glance. A wrong catalysis ratio could damage the hardening process.
- When removing already cured **Kerapoxy** from the joints, use a hot aired industrial drier. Remove hardened **Kerapoxy** from the tiles with **Pulicol**.
- When grouting large floor surface areas, it is recommended to use **Kerapoxy P**, available in grey (other colours are available upon request) because it is very fluid and easy to apply.

## APPLICATION PROCEDURE AS AN ACID-RESISTANT GROUT

### Preparing the joints

The joints must be dry, clean, free of dust and emptied at least 2/3 of the tile thickness. The excess adhesive or mortar should be removed while still fresh.

Before grouting, make sure that the installation mortar or the adhesive has set and released most of its moisture.

**Kerapoxy** is not affected by the moisture on the surface; the joints should not be wet during work.

### Preparing the mix

Pour all the hardener, component B, into a bucket containing component A and mix well until a smooth paste is obtained. For perfect mixing and avoiding overheating of the mixture, which could reduce working time, a low speed electric stirrer should be used. Use the paste within 45 minutes from mixing.

### Applying the grout

Spread **Kerapoxy** with the appropriate MAPEI float, making sure the joints are completely filled. Use the same float, but on edge, to remove excess grout.

### Finishing

After grouting with **Kerapoxy**, floors and walls should be cleaned immediately, before the product dries.

Wet the surface thoroughly and emulsify with a Scotch-Brite® pad, making sure not to wash-out the joints. When cleaning walls, the cleaning pad should be fully soaked with water. The excess liquid can be removed with a hard cellulose sponge (e.g. MAPEI sponge), and should be replaced when too full of resin. Use the same sponge for the final tooling of the grout.

It is very important that once the finishing process has ended, no traces of **Kerapoxy** are left on the tile surfaces because it will be very difficult to remove. It is therefore



## CHEMICAL RESISTANCE OF CERAMIC TILING GROUTED WITH KERAPOXY

PRODUCT				USE	
Group	Name	Concentration %	Laboratory benches	INDUSTRIAL FLOORING	
				Permanently used (+20°C)	Sporadically used (+20°C)
Acids	Acetic acid	2.5	+	+	+
		5	+	(+)	+
		10	-	-	-
	Hydrochloric acid	37	+	+	+
	Chromic acid	20	-	-	-
	Citric acid	10	+	(+)	+
	Formic acid	2.5	+	+	+
		10	-	-	-
	Lactic acid	2.5	+	+	+
		5	+	(+)	+
		10	(+)	-	(+)
	Nitric acid	25	+	(+)	+
		50	-	-	-
	Pure oleic acid	-	-	-	-
	Phosphoric acid	50	+	+	+
		75	(+)	-	(+)
	Sulphuric acid	1.5	+	+	+
		50	+	+	+
	96	-	-	-	
	Tannic acid	10	+	+	+
	Tartaric acid	10	+	+	+
	Oxalic acid	10	+	+	+
Alkalis	Ammonia in solution	25	+	+	+
	Caustic soda	50	+	+	+
	Sodium hypochlorite in solution:				
	active chlorine	6.4 g/l	+	(+)	+
	active chlorine	162 g/l	-	-	-
	Potassium permanganate	5	+	(+)	+
		10	(+)	-	(+)
	Potassium hydroxide	50	+	+	+
Sodium bisulphite	10	+	+	+	
Saturated solutions at 20°C	Sodium hyposulphite		+	+	+
	Calcium chloride		+	+	+
	Ferric chloride		+	+	+
	Sodium chloride		+	+	+
	Sodium chromate		+	+	+
	Sugar		+	+	+
	Aluminium sulphate		+	+	+
Oils and fuels	Petrol		+	(+)	+
	Oil of turpentine		+	+	+
	Diesel oil		+	+	+
	Coal-tar oil		+	(+)	(+)
	Olive oil		(+)	+	+
	Light fuel oil		+	+	+
	Heavy fuel oil		+	+	+
	Crude oil		+	+	+
Solvents	Acetone		-	-	-
	Ethylene glycol		+	+	+
	Glycerine		+	+	+
	Methylene glycol acetate		-	-	-
	Perchloroethylene		-	-	-
	Carbon tetrachloride		(+)	-	(+)
	Ethyl alcohol		+	(+)	+
	Trichloroethylene		-	-	-
	Chloroform		-	-	-
	Methylene chloride		-	-	-
	Tetrahydrofurane		-	-	-
	Toluene		-	-	-
	Carbon sulphide		(+)	-	(+)
	White spirit		+	+	+
	Benzene		-	-	-
	Trichloroethane		-	-	-
	Xylene		-	-	-
	Mercuric chloride (HgCl <sub>2</sub> )	5	+	+	+
	Hydrogen peroxide	1	+	+	+
		10	+	+	+
	25	+	(+)	+	

Legend: + excellent resistance

(+) good resistance

- poor resistance

## TECHNICAL DATA (typical values)

In compliance with:

- European EN 12004 as R2T
- ISO 13007-1 as R2T
- European EN 13888 as RG
- ISO 13007-1 as RG
- BS 5980-1980 type 5 class AA
- American ANSI A118.3 - 1992
- Canadian 71 GP 30 M type 1

### PRODUCT IDENTITY

	part A	part B
<b>Type:</b>	thick paste	dense liquid
<b>Colour:</b>	26 colours available	
<b>Density (g/cm<sup>3</sup>):</b>	1.64	0.97
<b>Dry solids content (%):</b>	100	100
<b>Brookfield viscosity (mPa·s)</b>	3500000	900
<b>Storage:</b>	24 months in a dry place in original packaging. Store part A at a temperature of at least +10°C to avoid crystallisation which, however, can be reversed by warming	
<b>Hazard classification according to 1999/45/EC:</b>	irritant	irritant Before using refer to the "Safety instructions for preparation and application" paragraph and the information on the packaging and Safety Data Sheet
<b>Customs class:</b>	3506 91 00	

### COMPOSITION AND PROPERTIES OF THE MIXTURE (at +23°C and 50% R.H.)

<b>Mix ratio:</b>	component A : component B = 9 : 1
<b>Consistency of mix:</b>	very pasty
<b>Density of mix (kg/m<sup>3</sup>):</b>	1,550
<b>Pot life:</b>	45 minutes
<b>Application temperature:</b>	from +12°C to +30°C
<b>Open time (as an adhesive):</b>	30 minutes
<b>Adjustability time (as an adhesive):</b>	60 minutes
<b>Set to light foot traffic:</b>	24 hours
<b>Ready for use:</b>	4 days

### FINAL PERFORMANCES

<b>Shear adhesion strength according to EN 12003 (N/mm<sup>2</sup>):</b>	
- initial:	25
- after water immersion:	23
- after thermal shock:	25
<b>Flexural strength (EN 12808-3) (N/mm<sup>2</sup>):</b>	31
<b>Compressive strength (EN 12808-3) (N/mm<sup>2</sup>):</b>	58
<b>Resistance to abrasion (EN 12808-3):</b>	147 (loss in mm <sup>3</sup> )
<b>Shrinkage (EN 12808-4) (mm/m):</b>	0.80
<b>Water absorption (EN 12808-5) (g):</b>	0.05
<b>Resistance to moisture:</b>	excellent
<b>Resistance to ageing:</b>	excellent
<b>Resistance to solvents and oils:</b>	very good (see table)
<b>Resistance to acids and alkali:</b>	excellent (see table)
<b>Temperature in use:</b>	from -20°C to +100°C



Finishing a porcelain tiled floor with single-brushed power float or rubber rake



Grouting a ceramic tile floor with wood inlays with a trowel



Finishing a ceramic tile floor with wood inlays with a sponge

## COVERAGE TABLE (kg/m<sup>2</sup>) DEPENDING ON THE SIZE OF THE TILE AND WIDTH OF THE JOINTS

Size of the tile (mm)	Width of the joint (mm):			
	3	5	8	10
75 X 150 X 6	0.6	1.0	–	–
100 X 100 X 6	0.6	1.0	–	–
100 X 100 X 10	1.0	1.6	–	–
100 X 200 X 6	0.5	0.8	–	–
100 X 200 X 10		1.2	2.0	2.4
150 X 150 X 6	0.4	0.7	–	–
200 X 200 X 8	0.4	0.7	–	–
120 X 240 X 12	–	1.2	2.0	2.4
250 X 250 X 12	–	0.8	1.3	1.6
250 X 330 X 8	0.3	0.5	0.8	0.9
300 X 300 X 8	0.3	0.5	0.7	0.9
300 X 300 X 10	0.4	0.6	0.9	1.1
300 X 600 X 10	0.3	0.4	0.7	0.8
330 X 330 X 10	0.3	0.5	0.8	1.0
400 X 400 X 10	0.3	0.4	0.7	0.8
450 X 450 X 12	–	0.5	0.7	0.9
500 X 500 X 12	–	0.4	0.6	0.8
600 X 600 X 12	–	0.4	0.5	0.7

### FORMULA FOR THE COVERAGE CALCULATION:

$$\frac{(A + B)}{(A \times B)} \times C \times D \times 1.6 = \frac{\text{kg}}{\text{m}^2}$$

- A = length of tile (in mm)
- B = width of tile (in mm)
- C = thickness of tile (in mm)
- D = width of joint (in mm)

necessary to frequently rinse the sponge with clean water during the cleaning process.

When finishing large floor surface areas, use a rotary, disc-type power float with Scotch-Brite® abrasive pads, well saturated with water.

All excess liquid can be removed with a rubber squeegee. If too much time has elapsed since installation and **Kerapoxy** has already begun to set, add 10% alcohol to the cleaning water.

### APPLICATION PROCEDURE AS AN ADHESIVE

After mixing the two components as described above, spread the adhesive with a notched trowel. Apply the surfacing material under firm pressure to ensure good contact. After setting, bonding becomes extremely strong and resistant to chemical agents.

### SET TO LIGHT FOOT TRAFFIC

At +20°C, floors are set to light foot traffic after 24 hours.

### READY FOR USE

4 days. Surfaces can also undergo chemical attack after 4 days.

### Cleaning

Clean tools and containers with plenty of water before **Kerapoxy** hardens. When **Kerapoxy** has hardened, cleaning can only be done by mechanical means or with **Pulicol**.

### CONSUMPTION

Consumption of **Kerapoxy** varies depending on the width of the joints, the size and thickness of the tiles. Some examples of consumption in kg/m<sup>2</sup> are shown in the chart.



An example of a grouted battery room



An example of grouted ornamental stones



An example of a bonded and grouted kitchen worktop

# Kerapoxy

## PACKAGING

**Kerapoxy** is supplied, with mixing proportions carefully measured, in drums containing component A and bottles of component B. The total weight of the units is: 10, 5 and 2 kg in total.

## COLOURS

**Kerapoxy** is available in 26 colours from the "MAPEI COLOURED GROUTS" range.

## STORAGE

**Kerapoxy** can be stored 24 months in a dry place in original packaging. Store component A at a temperature of at least +10°C to avoid crystallisation which, however, can be reversed by warming.

## INSTRUCTIONS FOR PREPARATION AND APPLICATION

Irritant for eyes, respiratory tract and skin. May cause sensitisation by skin contact. In case of contact with eyes, wash immediately with plenty of water and consult a doctor. Use protective clothing, gloves and goggles. **Kerapoxy** is dangerous for the environment.

Avoid release of the product to the environment and dispose as hazardous waste.

PRODUCT FOR PROFESSIONAL USE.

## WARNING

*Although the technical details and recommendations contained in this data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.*

**All relevant references for the product are available upon request and from [www.mapei.com](http://www.mapei.com)**



An example of a grouted brewery floor



An example of a grouted wine cellar floor



BUILDING THE FUTURE