



Adesilex P4



High performance, rapid-setting, full contact, cementitious adhesive for ceramic tile and stone material installations; smoothing compound for interiors and exteriors; mortar for brick and concrete block walls



CLASSIFICATION IN COMPLIANCE WITH EN 12004

Adesilex P4 is an improved (C2) fast setting (F) cementitious adhesive of class C2F.

WHERE TO USE

Tile and stone flooring installations

- Floor bonding of all types of medium and large ceramic tiles, natural stone (if not sensitive to moisture or subject to surface efflorescence), terracotta, and terrazzo in interiors and exteriors.

Smoothing compounds

- Interior and exterior smoothing of all substrates generally used in building, provided they are clean, such as concrete slabs, cementitious screeds, and existing ceramic tile, terrazzo and natural stone floors.

Brick and concrete block walls

- Expansive mortar for brick or concrete block walls.

Some application examples

- Total bonding of large size porcelain tiles on floors subject to heavy traffic, such as offices, shopping malls, hospitals and schools.
- Bonding of stone material and terrazzo, including large sizes.
- Setting quarry tiles, klinker or single-fired tiles on terraces and balconies.
- Setting ceramic tiles of every type over all kinds of underfloor heating installations.

- Overlapping of ceramic tiles and stone material on old floors (ceramic, natural stone, cement, terrazzo), as long as they are solid and perfectly clean.
- Easy levelling and localised smoothing with rapid curing prior to setting ceramic tiles.
- Rapid replacement of tiles, when filling irregularities in the substrate is required at the same time.
- Bonding of brick and concrete blocks for building walls rapidly.

TECHNICAL CHARACTERISTICS

Adesilex P4 is a grey powder composed of cement and fine-graded mineral fillers, containing high quantities of synthetic resins and special additives according to a formula developed in the Mapei Research Laboratories.

Mixed with water, Adesilex P4 becomes a mortar with the following properties:

- semi-fluid and easily trowellable;
- 100% back-buttering is guaranteed. With Adesilex P4 it is possible to obtain adhesive beds 3 mm to 20 mm thick without undulations, ideal for external installations and heavy traffic areas;
- able to absorb deflections of the substrate and tiles;
- perfect bonding to all materials generally used in building;
- cures rapidly without significant shrinkage until it becomes quite strong;



Adesilex P4

- waterproof, weatherproof and resistant to frost.

RECOMMENDATIONS

Do not use **Adesilex P4**:

- on walls or slanted surfaces;
- wood and wood conglomerates;
- metal surfaces, rubber, PVC or linoleum;
- with natural or artificial stone material slabs subject to movement due to moisture.

APPLICATION PROCEDURE

FLOOR INSTALLATION

Preparing the substrate

The substrate must be cured, mechanically strong, free of loose materials, grease, oils, paint, wax and sufficiently dry. Cementitious substrates should not be subject to shrinkage after the installation of ceramic tiles. During spring and summer, the cementitious screeds must be cured for at least 28 days, unless they are not made with MAPEI special binders for screeds, such as **Mapcem**, **Topcem** or with **Topcem Pronto**.

Dampen with water to cool the surfaces that have been heated by the exposure to sunlight. Gypsum substrates and anhydrite screeds must be perfectly clean, sufficiently hard and free of dust. It is absolutely essential to treat them with **Primer G** or **Mapeprim SP**. Areas subject to high humidity must be treated with **Primer S**.

Preparing the mix

Mix **Adesilex P4** in a clean receptacle with 5-5.5 litres of clean water for every 25 kg bag until a smooth lump-free paste is obtained. Let the mix sit for 3 minutes, then stir again, and the mix is ready for use. Mixed this way **Adesilex P4** will have a pot life of approx. 60 minutes at +23°C and 50% R.H. If both adhesive and tiles are very thick, or the tiles are particularly heavy, 20% of suitably graded clean sand may be added to prevent shrinkage or settling.

Applying the mix

Apply **Adesilex P4** to the substrate with a suitable trowel. The selection of the correct trowel depends on the evenness of the substrate, the size of the tile and the profile of the back. For flat surfaces and medium size tiles use MAPEI trowel No. 6 or No. 10 (consumption approx. 3-5 kg/m²). For uneven surfaces, large size tiles, tiles with highly profiled ribs or lugs, MAPEI trowel No. 10 or a round-notched trowel is recommended (consumption approx. 5-10 kg/m²). Consumption is generally 1.4 kg/m² for each mm of thickness.

Installing the tiles

It is not necessary to wet the tiles before setting. Only when the backs are very dusty is it advisable to dip the tiles in clean water. Set the tiles on the bed of **Adesilex P4** without pressure but with a light hand movement to ensure 100% coverage. The open time of **Adesilex P4** in normal temperatures and humidity is approx. 15 minutes. Unfavourable weather conditions (strong sun, drying wind, high temperature)

may shorten the open time, sometimes quite drastically, to just a few minutes. For this reason, constant checks must be made to see if the adhesive has formed a surface skin or is still "fresh" to the touch. Wetting the substrate before applying the adhesive helps to lengthen the open time. However if a surface skin has formed, retrowel on the adhesive with a notched trowel.

It is not advisable to wet the adhesive once it has formed a skin because, instead of dissolving the skin, a non-adhesive film will be formed.

Any necessary adjustment of the tiles should be carried out within 30 minutes after setting, after which time adjustment becomes problematic.

Tiles set with **Adesilex P4** must not be subject to washout or rain for 3 hours at a temperature of +23°C and must be protected from frost and hot sun for at least 24 hours after installing.

GROUTING AND SEALING

Joints between the tiles can be grouted after 4 hours with the specific MAPEI cementitious or epoxy grouts, available in different colours. Expansion joints must be sealed with the specific MAPEI sealants.

SET TO LIGHT FOOT TRAFFIC

Floors are set to light foot traffic after approximately 4 hours.

READY FOR USE

The surfaces are ready for use after approx. 24 hours.

SMOOTHING

Preparing the substrate

Substrates must be level, solid, consistent and free of loose materials, grease, oils, paint, wax, etc. and sufficiently dry. Anhydrite substrates must be thoroughly dry, sufficiently hard and free of dust (check for residual moisture) and must be previously treated with **Primer G**.

Substrates in very damp areas must first be treated with **Primer S** or **Mapeprim SP**.

Preparing the mix

Mix **Adesilex P4** in a clean receptacle with 5-5.5 litres of clean water for every 25 kg bag until a smooth lump-free paste is obtained. Let the mix sit for 3 minutes, then stir again and the mix is ready for use. Mixed this way **Adesilex P4** will have a pot life of approx. 60 minutes at +23°C and 50% R.H.

Applying the mix

Apply the mix with a long metal trowel. When needed, additional coats may be applied in rapid succession as soon as the previous coat has hardened.

Installing the tiles

The surface can be tiled over as soon as it has hardened (3 to 4 hours, depending on the temperature and the absorbency of the substrate).

BRICK AND CEMENT BLOCK WALLS

Preparing the mix

Adesilex P4 should be mixed in a clean receptacle with 5-5.5 litres of clean water for



Mixing Adesilex P4



Spreading with semicircular notched trowel



Laying large size tiles

TECHNICAL DATA (typical values)

Adesilex P4 complies with:

- EN 12004 as C2F
- American ANSI A118.4 - 1999
- Canadian 71 GP 30 M type 2

PRODUCT IDENTITY

Consistency:	powder
Colour:	grey
Bulk mass density (kg/m³):	1300
Dry solids content (%):	100
Storage:	12 months in a dry place in the original unopened packing
Hazard classification according to EC 99/45:	irritant. Before using refer to the "Safety Instructions for the preparation and application" paragraph and the information on the packing and safety data sheet
Customs class:	3824 50 90

COMPOSITION AND PROPERTIES OF THE MIXTURE at +23°C - 50% R.H.


Mix ratio:	20-22 parts water to 100 parts of Adesilex P4
Consistency of the mix:	semi-fluid
Mass density of the mix (kg/m³):	1700
pH of the mix:	12
Pot life of the mix:	60 minutes
Application temperature range:	from +5°C to +30°C
Open time:	approx. 15 minutes
Setting time: a) initial: b) final:	100 minutes 150 minutes
Adjustability time:	approx. 30 minutes
Set to light foot traffic:	4 hours
Grouting:	4 hours
Ready for use:	24 hours

FINAL PERFORMANCES

Adhesion (according to EN 1348) (N/mm²): - initial (after 28 days at +23°C - 50% R.H.): - after heat ageing: - after water immersion: - after freeze-thaw cycles:	2.0 1.9 1.3 1.2
Compressive strength (after 28 days) (N/mm²):	14.0
Flexural strength (after 28 days) (N/mm²):	5.0
Resistance to damp:	excellent
Resistance to ageing:	excellent
Resistance to solvents and oils:	excellent
Resistance to acids and alkali:	poor
Resistance to temperature:	from -30°C to +90°C



Laying porcelain tiles



Smoothing existing flooring with Adesilex P4



Dipping a concrete block in Adesilex P4

Adesilex P4

every 25 kg bag until a smooth lump-free mix is obtained. Let the mix sit for 3 minutes then stir again and the mix is ready for use. **Adesilex P4** has a pot life of approx. 60 minutes at +23°C and 50% R.H.

Laying brick or concrete blocks

Pour the **Adesilex P4** mix into a receptacle large enough for the size and shape of the brick or cement blocks. Place the brick or concrete block on the surface of the mix so the adhesive is transferred. Place the brick or block on the wall. This method cuts completion time by half.

Cleaning

Tools and hands may be cleaned with abundant water. Tiles may be cleaned with a damp sponge; only after a few hours may a little water be used.

CONSUMPTION

Flooring installations

- Medium size tiles on smooth surfaces (with No. 6 or No. 10 trowel): approx. 3-5 kg/m².
- Large tiles or uneven surfaces (No. 10 trowel or **Adesilex P4** trowel): approx. 5-10 kg/m².

Smoothing

Approx. 1.4 kg/m² for each mm of thickness.

Brick and concrete block walls

As needed, depending on the size.

PACKAGING

Adesilex P4 is available in 25 kg paper bags.

STORAGE

12 months in a dry place in the original unopened packaging.

SAFETY INSTRUCTIONS FOR THE PREPARATION AND APPLICATION


It contains cement that, when in contact with sweat or other bodily fluids, produce an irritant alkaline reaction and allergic reactions to those predisposed. It is highly recommended to use gloves and eye protection. For further information refer to the safety data sheet.

FOR PROFESSIONALS.

WARNING

Although the technical details and recommendations contained in this report correspond to the best of our knowledge and experience, all the above information must, in every case be taken as merely indicative and subject to confirmation after long-term practical applications; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

All relevant references of the product are available upon request



Comparison of back-wetting between a normal adhesive and Adesilex P4



BUILDING THE FUTURE

MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)

MAPEI S.p.A. - ITALY				MAPEI CORP - U.S.A.	MAPEI FAR EAST Pte Ltd MAPEI MALAYSIA SDN BHD		MAPEI s.r.o. - CZECH REP.
MAPEI FRANCE	MAPEI INC - CANADA	RESCON MAPEI AS - NORWAY		MAPEI Kft. - HUNGARY	MAPEI ARGENTINA S.A.	MAPEI SUISSE SA	

www.mapei.com