

Mapecem Pronto



**Pre-blended,
ready-to-use,
quick-setting and
drying (24 hours),
controlled-shrinkage
mortar for screeds**



CLASSIFICATION ACCORDING TO EN 13813

Screeds made using **Mapecem Pronto** according to the specifications in this Technical Data Sheet are classified as CT - C60 - F10 - A1_{fl} in accordance with European Standard EN 13813.

WHERE TO USE

Internal and external floating and bonded screeds on old and new floor slabs, for laying wood, PVC, linoleum, carpet, ceramic, natural stone and any other type of floor covering where quick drying is required for immediate laying of the floor covering.

Some application examples

- Screeds ready for foot traffic after 2-3 hours, and dry after 24 hours.
- Screeds on which it is possible to lay ceramic tiles after 3 hours.
- Screeds on which it is possible to lay PVC, linoleum, wood and natural and artificial stone material after only 24 hours (residual moisture lower than 2%).
- Repairs and renovation of screeds in areas subject to continuous traffic (e.g. supermarkets, hospitals, airports etc.).
- Screeds incorporating heating systems.

TECHNICAL CHARACTERISTICS

Mapecem Pronto is a pre-blended, ready-to-use, quick-setting and drying, controlled-shrinkage mortar with a special hydraulic binder base, additives and selected aggregates to be mixed with water.

Mapecem Pronto is extremely easy to use, in that it is

simply mixed with water. This means that human error due to incorrect dosage of the binder and choice of aggregates is avoided, which could compromise the final characteristics of the screed once it has set.

Mapecem Pronto is the ideal solution where finding good quality inert material of the correct grade is difficult, or in the case of installations in areas, such as historical town centres, where transportation and preparation of the blend with traditional binders becomes problematic.

RECOMMENDATIONS

- Do not use **Mapecem Pronto** on screeds subject to rising damp (lay a vapour barrier).
- Do not mix **Mapecem Pronto** with other binders (e.g. **Topcem**, cement, lime, gypsum etc.) or aggregates.
- Mix **Mapecem Pronto** with the correct amount of water.
- Do not add water and do not re-mix mortar prepared using **Mapecem Pronto** if it has already started to set.
- Do not wet the surface of screeds made using **Mapecem Pronto**.
- Blended **Mapecem Pronto** can not be transported as it is a fast set product.

HOW TO USE

Preparation of the substrate

All types of substrate are suitable for installing screeds made using **Mapecem Pronto**.

In those cases where quick drying is required, if there is moisture present in the substrate, screeds made using **Mapecem Pronto** must be isolated with a suitable vapour barrier, and must be at least 35 mm thick for floor coverings subject to foot traffic. For screeds bonded to the substrate (thicknesses lower than 35 mm), check beforehand that they are dry and free of cracks, powder, loose parts, paint, wax, oil and traces of grease.

Preparation of the mix

Mapecem Pronto mix may be prepared with one of the following:

- paddle mixer;
- drum mixer;
- forced action mixer.

Mix a 25 kg bag of **Mapecem Pronto** with 2.1-2.3 l of water for 3-4 minutes.

The amount of water must not be modified for any reason, otherwise the final performance characteristics will be compromised.

Tamp and float the mix until a smooth, closed, surface without residual water is obtained.

Each mix must be poured and tamped as quickly as possible, and after no more than 30 minutes from the start of preparation. The surrounding temperature influences the setting and drying times of screeds made using **Mapecem Pronto**.

FLOATING SCREEDS (thickness from 35 to 60 mm)

Mapecem Pronto mix must be laid on an isolating layer made up of polythene sheets or a similar material in order to allow for movement between the screed and the existing substrate. In case of rising damp, the aforementioned isolating layer must be formed using a sufficiently waterproof membrane to form an efficient vapour barrier. The areas of the **Mapecem Pronto** screed which have pipe-work running through them must be reinforced by positioning light, metallic reinforcement (e.g. electro-welded hexagonal mesh).

The laying of screeds made by **Mapecem Pronto** is carried out using the same technique as for cementitious screeds. Prepare a series of level guides, spread the mix and tamp thoroughly before finishing off with a float, to obtain a better surface finish. Around the perimeter of the room and around columns which run through the floor, it is good practice to place 1cm-thick isolating material (such as polystyrene, cork, etc.) before casting.

If work is interrupted, cut the screed perpendicularly to the substrate and insert a series of 3-6 mm diameter, 20-30 cm-long steel rods in the screed at a pitch of 20-30 cm. This operation will guarantee a good weld between the construction joints, and avoid cracking and uneven joints.

BONDED SCREEDS (thickness up to 35 mm)

Screeds with a lower thickness must be bonded to the substrate, which may be either a cementitious type or made up of existing flooring in ceramic or stone material. If another type of substrate is present, please consult the MAPEI Technical Service Department. Once the substrate has been cleaned down,

and immediately before laying the screed made from **Mapecem Pronto**, prepare the bonding slurry according to the proportions illustrated in the following table, and spread it on using a brush or a trowel.

In order to guarantee perfect bonding, spread the **Mapecem Pronto** mortar on the bonding slurry while it is still fresh (fresh on fresh).

The preparation, dosage and laying of the **Mapecem Pronto** mix are exactly the same as described above.

Dosage of the bonding slurry

Mix until completely homogenous:

Planicrete:	1 part in weight
Water:	1 part in weight
Mapecem Pronto:	8 parts in weight

This mix tends to settle. Remix before application.

MEASURING MOISTURE CONTENT

Measurements of the residual moisture using an electronic hygrometer give values which are for indication purposes only. Therefore, to measure the level of residual moisture, it is necessary to use a carbide hygrometer.

CONSUMPTION

The consumption of **Mapecem Pronto** is approximately 20 kg/m² per cm of thickness, according to how much tamping is carried out.

Cleaning

Tools may be cleaned using water.

PACKAGING

Mapecem Pronto is available in 25 kg bags.

STORAGE

Mapecem Pronto remains stable for at least 12 months if stored in a dry place.

SAFETY INSTRUCTIONS FOR THE PREPARATION AND APPLICATION

The product contains hydraulic binders that when in contact with sweat or other body fluids, could produce an alkaline reaction which is slightly irritant.

Use protective gloves and goggles.

For further information, please refer to the safety data sheet.

FOR PROFESSIONALS.

WARNING

While the indications and guidelines contained in this data sheet correspond to the company's knowledge and wide experience, they must be considered, under all circumstances, merely as an indication and subject to confirmation only after long-term, practical applications. Therefore, anybody who undertakes to use this product, must ensure beforehand that it is suitable for the intended application and, in all cases, the user is to be held responsible for any consequences deriving from its use.

**All relevant references
of the product are available
upon request**

TECHNICAL DATA (typical values)

Conforms to Standard:

– European EN 13813 CT - C60 - F10 - A1n

PRODUCT DETAILS

Consistency:	powder
Colour:	grey
Bulk density (kg/m³):	1800
Dry solids content (%):	100
Shelf life:	12 months in original packaging in a dry place
Hazard classification according to Directive 99/45/CE:	none. Before using refer to the "Safety instructions for the preparation and application" paragraph and the information on the packing and Safety Data Sheet
Customs class:	3824 50 90

APPLICATION DATA at +23°C - 50% R.H.

Mixing ratio:	2.1-2.3 l of water for each 25 kg bag of Mapecem Pronto
Density of the mix (g/cm³):	approx. 2200
Mixing time:	3-4 minutes
Pot life of mix:	20-30 minutes
Application temperature range:	from +5°C to +35°C
Set to light foot traffic:	after 2-3 hours
Waiting time before installation:	3 hours for ceramic and natural stone. 24 hours for resilient materials and wood
Waiting time before levelling:	after 4 hours
Residual moisture after 24 hours (%):	< 2

FINAL PERFORMANCES

Resistance to acids:	fair
Resistance to alkalis:	excellent
Resistance to oil:	excellent
Resistance to solvents:	excellent
In-service temperature range:	from -30°C to +90°C
Mechanical strength:	see table below

Compressive strength, flexural strength and residual moisture	Compressive strength (N/mm ²)	Flexural strength (N/mm ²)	Residual moisture (%)
– after 1 day:	> 40	> 6	< 2.0
– after 3 days:	> 50	> 7	< 1.6
– after 28 days:	> 62	> 10	< 1.5

Mapecem Pronto



BUILDING THE FUTURE

MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)

<p>CERTQUALITY No. 250</p>	<p>The Mapei Environmental Management System ISO 14001 Plant in Bologna di Modigliana CERTQUALITY No. 1230</p>	<p>The Mapei Environmental Management System ISO 14001 Plant in Latina CERTQUALITY No. 8127</p>	<p>EMAS VERIFIED ENVIRONMENTAL MANAGEMENT SYSTEM No. 1000013 PLANT IN MODIGLIANA</p>	<p>OCCUPATIONAL HEALTH AND SAFETY MANAGEMENT SYSTEMS OHSAS 18001 CERTIFIED BY CERTIQUALITY No. 5580 PLANT IN MODIGLIANA</p>	<p>CERTQUALITY No. 6853</p>	<p>CERTQUALITY No. 3358</p>	<p>ITC No. 03 0063 SJ</p>
MAPEI S.p.A. - ITALY				MAPEI CORP - U.S.A.	MAPEI FAR EAST Pte Ltd MAPEI MALAYSIA SDN BHD		MAPEI s.r.o. - CZECH REP.
<p>CERTQUALITY No. 1517</p>	<p>QMI No. 004157</p>	<p>DNV No. 94-OSL-AQ-6236</p>	<p>The Mapei Environmental Management System ISO 14001 Plant in Sogno DNV No. 2002-GR-1511-0141</p>	<p>EMAS VERIFIED ENVIRONMENTAL MANAGEMENT SYSTEM No. 2003-GR-AC-9111 PLANT IN SAGUNTA</p>	<p>DNV No. 12026-2002 AQ-BUD-TGA</p>	<p>IRAM No. AR-QS-688</p>	<p>CERTQUALITY No. 5776</p>
MAPEI FRANCE	MAPEI INC - CANADA	RESCON MAPEI AS - NORWAY			MAPEI Kft. - HUNGARY	MAPEI ARGENTINA S.A.	MAPEI SUISSE SA

www.mapei.com